

**IN THE CLAIMS:**

This listing of claims will replace all prior versions, and listings, of claims in the application:

Claims 1 and 4-8 have been amended, claims 2-3 and 9-11 have been canceled and claims 12-23 have been added as follows:

**Listing of Claims:**

Claim 1 (currently amended): A deodorizing filter comprising a first deodorizing filter regulated so as to have a high-pH environment and a second deodorizing filter regulated so as to have a low-pH environment,

wherein the first deodorizing filter and/or the second deodorizing filter are filters of a cobalt phthalocyanine complex and an iron phthalocyanine complex supported on an active-carbon-filled paper.

Claim 2 (canceled)

Claim 3 (canceled)

Claim 4 (currently amended): The deodorizing filter as recited in ~~any one of claims 1 to 3~~ claim 1, wherein the ~~first deodorizing filter and/or the second deodorizing filter are filters of a cobalt phthalocyanine complex and an iron phthalocyanine complex supported on an active-carbon-filled~~ paper weight ratio of the complexes supported, cobalt phthalocyanine complex/iron phthalocyanine

complex, is 98/2 to 55/45.

Claim 5 (currently amended): The deodorizing filter as recited in ~~any one of claims 1 to 3~~ claim 1, wherein the ~~first deodorizing filter is a filter of a cobalt phthalocyanine complex and an iron phthalocyanine complex supported on an active-carbon-filled paper~~ weight ratio of the complexes supported, cobalt phthalocyanine complex/iron phthalocyanine complex, is 95/5 to 85/15.

Claim 6 (current amended): The deodorizing filter as recited in claim 1, wherein the ~~first deodorizing filter and the second deodorizing filter are filters of a cobalt phthalocyanine complex and an iron phthalocyanine complex supported on an active-carbon-filled paper~~ pH of the high-pH environment is 7.5 to 12.0 and the pH of the low-pH environment is 1.5 to 5.0.

Claim 7 (currently amended): The deodorizing filter as recited in ~~any one of claims 4 to 6~~ claim 1, wherein the ~~weight ratio of the complexes supported, cobalt phthalocyanine complex/iron phthalocyanine complex, is 98/2 to 55/45~~ amount of the complexes supported is in the range of 200 to 20,000  $\mu$ g with respect to 1 g of the active-carbon-filled paper.

Claim 8 (currently amended): The deodorizing filter as recited in ~~any one of claims 4 to 7~~ claim 1, wherein the ~~weight ratio of the complexes supported, cobalt phthalocyanine complex/iron phthalocyanine complex, is 95/5 to 85/15~~ active-carbon-filled paper contains active-carbon at a content of 40 to 80 mass %.

Claim 9 (canceled)

Claim 10 (canceled)

Claim 11 (canceled)

Claim 12 (new): A deodorizing filter comprising a first deodorizing filter regulated so as to have a high-pH environment and a second deodorizing filter regulated so as to have a low-pH environment,

wherein the first deodorizing filter is a filter of a cobalt phthalocyanine complex and an iron phthalocyanine complex supported on an active-carbon-filled paper.

Claim 13 (new): The deodorizing filter as recited in claim 12, wherein the weight ratio of the complexes supported, cobalt phthalocyanine complex/iron phthalocyanine complex, is 98/2 to 55/45.

Claim 14 (new): The deodorizing filter as recited in claim 12, wherein the weight ratio of the complexes supported, cobalt phthalocyanine complex/iron phthalocyanine complex, is 95/5 to 85/15.

Claim 15 (new): The deodorizing filter as recited in claim 12, wherein the pH of the high-pH environment is 7.5 to 12.0 and the pH of the low pH environment is 1.5 to 5.0.

Claim 16 (new): The deodorizing filter as recited in claim 12, wherein the amount of the complexes supported is in the range of 200 to 20,000  $\mu\text{g}$  with respect to 1 g of the active-carbon-filled paper.

Claim 17 (new): The deodorizing filter as recited in claim 12, wherein the active-carbon-filled paper contains active-carbon at a content of 40 to 80 mass %.

Claim 18 (new): A deodorizing filter comprising a first deodorizing filter regulated so as to have a high-pH environment and a second deodorizing filter regulated so as to have a low-pH environment,

wherein the first deodorizing filter and the second deodorizing filter are filters of a cobalt phthalocyanine complex and an iron phthalocyanine complex supported on an active-carbon-filled paper.

Claim 19 (new): The deodorizing filter as recited in claim 18, wherein the weight ratio of the complexes supported, cobalt phthalocyanine complex/iron phthalocyanine complex, is 98/2 to 55/45.

Claim 20 (new): The deodorizing filter as recited in claim 18, wherein the weight ratio of the complexes supported, cobalt phthalocyanine complex/iron phthalocyanine complex, is 95/5 to 85/15.

Claim 21 (new): The deodorizing filter as recited in claim 18, wherein the pH of the high-pH environment is 7.5 to 12.0 and the pH of the low pH environment is 1.5 to 5.0.

Claim 22 (new): The deodorizing filter as recited in claim 18, wherein the amount of the complexes supported is in the range of 200 to 20,000  $\mu\text{g}$  with respect to 1 g of the active-carbon-filled paper.

Claim 23 (new): The deodorizing filter as recited in claim 18, wherein the active-carbon-filled paper contains active-carbon at a content of 40 to 80 mass %.